least one roll to transmit a rotation of the roll to the pipe, wherein the polytetrafluoroethylene block-shaped molded article is produced and has a melt viscosity and a block deformation amount contained within a polygonal region surrounded by a straight line A: $x = 1.0 \times 10^9$ (melt viscosity of 1.0×10^9 poise), a straight line B: $x = 2.5 \times 10^{10}$ (melt viscosity of 2.5×10^{10} poise), a straight line C1: $y = 7.0$ (block deformation amount of 7.0%), a straight line D1: $y = 0$ (block deformation amount of 0%), and a straight line E1: $y = -8.7 Log_{10}(x) + 91$ in a graph with an x-axis being a common logarithm of the melt viscosity (poise) at 380°C of polytetrafluoroethylene and a y-axis being the block deformation amount (%) which is a weight loss until a stable film or sheet can be cut from the molded article.